



PB21002F

DESCRIPTION

Compression molded virgin Fluorinate Ethylene-Propylene (FEP) copolymer.

TYPICAL PROPERTIES

Property	Test Method	Units	Typical Value
Color	-	-	Translucid
Specific Gravity	ASTM D792	-	2.14
Hardness Shore D	ASTM D2240	Shore D	57 _(peak) / 53 _(sustained)
Tensile Strength	ASTM D2116	PSI [MPa]	4,165 [29]
Elongation at Break	ASTM D2116	%	370

REQUIREMENTS

This product meets ASTM D2116 Type IV requirements.