



PB10300

DESCRIPTION

Compression molded 5% glass fiber 5% MoS₂ filled PolyTetraFluoroEthylene (PTFE).

TYPICAL PROPERTIES

Property	Test Method	Units	Typical Value
Color	-	-	Grey
Specific Gravity	ASTM D792	-	2.24
Hardness Shore D	ASTM D2240	Shore D	64 _(peak) / 56 _(sustained)
Tensile Strength	ASTM D4745	PSI [MPa]	3,350 [23]
Elongation at Break	ASTM D4745	%	240

REQUIREMENTS

This product meets ASTM D4745 Type I Grade 4 requirements.