



PB10303

DESCRIPTION

Compression molded 15% glass fiber 5% MoS₂ filled PolyTetraFluoroEthylene (PTFE).

TYPICAL PROPERTIES

Property	Test Method	Units	Typical Value
Color	-	-	Light Grey
Specific Gravity	ASTM D792	-	2.28
Hardness Shore D	ASTM D2240	Shore D	67 _(peak) / 59 _(sustained)
Tensile Strength	ASTM D4745	PSI [MPa]	2,525 [17]
Elongation at Break	ASTM D4745	%	185

REQUIREMENTS

This product meets ASTM D4745 Type I Grade 5 and AMS 3678/3 requirements.